



Crypton Belgium bv
Industrielaan 105 / 3
8930 MENEN

Your notice of
 25-08-2021

Your reference

Date
 15-09-2021

Analysis Report 21.05399.05

Required tests :

EN 1021-1 (2014)

EN 1021-1 (2014)

EN 1021-2 (2014)

Water soaking procedure

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette


Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match flame equivalent

Sample id	Information given by the client	Date of receipt
T2118409	CRYPTON NAME MAZIN - CUSTOMER ARISTIDE NAME PLANET	25-08-2021



Mike De Vrieze
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2118409 - CRYPTON NAME MAZIN - CUSTOMER ARISTIDE NAME PLANET

Water soaking procedure

Date of ending the test 30-08-2021
Standard used EN 1021-1 (2014)/EN 1021-2 (2014)

Deviation from the standard -

The water soaking procedure* is compatible with following standard(s):

EN 1021-1 Ann.D (2014)

EN 1021-2 Ann.D (2014)

* Has been carried out based on information given by the client

Sample generated: T2118409_01d



**Reference: T2118409_01d - CRYPTON NAME MAZIN - CUSTOMER ARISTIDE
 NAME PLANET**

**Furniture - Assessment of the ignitability of upholstered furniture - Ignition source :
 smouldering cigarette**

Date of ending the test 03-09-2021
 Standard used EN 1021-1 (2014)
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%
 Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³

	1#	2#	3#
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoulders more than 1 hour	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Occurrence of flames	no	no	no
	non-ignition	non-ignition	non-ignition

cigarette fails to smoulder its complete length

Conclusion Non-ignition

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

**Reference: T2118409_01d - CRYPTON NAME MAZIN - CUSTOMER ARISTIDE
NAME PLANET**

**Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match
flame equivalent**

Date of ending the test 03-09-2021
Standard used EN 1021-2 (2014)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%
Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³
Flame application time (s) 15

	1	2	3
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoke/heat/glowing more than 60 min	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Flames to extremities	no	no	no
Flames through thickness	no	no	no
Flaming > 120 s	no	no	no
Afterflame time (s)	0	0	1
	non-ignition	non-ignition	non-ignition

Conclusion Non-ignition

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.