Aristide nv **Dhr. Rudy Vuerinckx** Nachtegaalstraat 109 **2550 KONTICH** 



Your notice of 14-04-2016

Your reference

Date 19-04-2016

# Analysis Report 16.01922.06

#### Translation of analysis report 16.01922.03, made on 19-04-2016

#### Required tests:

IMO - 2010 FTP Code Annex 1 -Fire test procedures - Part 8

IMO - 2010 FTP Code Annex 1 -

Fire test procedures - Part 8

Fire tests - Test for upholstered furniture - smouldering

cigarette test

Fire tests - Test for upholstered furniture - Match flame

equivalent

Identification number	Information given by the client	Date of receipt
T1607474	WILLIAM	14-04-2016

Petra Wittevrongel

#### Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

## $\textbf{CENTEXBEL} \bullet \textbf{textile competence centre} \bullet \textbf{www.centexbel.be} \bullet \textbf{www.vkc.be}$

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947 GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Analysis Report 16.01922.06 Date 19-04-2016 Page 2/4

**Reference:** T1607474 - WILLIAM

## IMO upholstered furniture

# Information given by the client

Type of furniture Seat / sofa

**Fabric** 

Composition 60% PES - 40% CO

Structure Weave
Weight per unit area 760 g/m²
Treated with an FR finish/coating yes

**Reference:** T1607474 - WILLIAM

## Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test 19-04-2016

Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures -

Part 8

Deviation from the standard

Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling T 23140 (Recticel) \* - non-fire retardant foam -  $\pm$  22

kg/m<sup>3</sup>

\* standard non-FR PU-foam (as indicated in Appendix 2

and 3 of Part 8)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurence of flames	no	no
	non-ignition	non-ignition

**Conclusion** Pass

Performed under accreditation in the fire lab under the responsibility of Nathan De Kock

**Reference:** T1607474 - WILLIAM

## Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 19-04-2016

Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures -

Part 8

Deviation from the standard

Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling T 23140 (Recticel) \* - non-fire retardant foam -  $\pm$  22

kg/m³

\* standard non-FR PU-foam (as indicated in Appendix 2

and 3 of Part 8)

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	15
	non-ignition	non-ignition

**Conclusion** Pass

Performed under accreditation in the fire lab under the responsibility of Nathan De Kock